

PGPUB-DOCUMENT-NUMBER: 20020061449

PGPUB-FILING-TYPE: new

DOCUMENT-IDENTIFIER: US 20020061449 A1

TITLE: Ion-conductive composition, gel electrolyte,  
non-aqueous electrolyte battery, and electrical  
double-layer capacitor

PUBLICATION-DATE: May 23, 2002

INVENTOR-INFORMATION:

NAME	CITY	STATE	COUNTRY
RULE-47			
Maruo, Tatsuya	Chiba-shi		JP
Yoshida, Hiroshi	Chiba-shi		JP
Sato, Takaya	Chiba-shi		JP

APPL-NO: 09/ 955432

DATE FILED: September 19, 2001

FOREIGN-APPL-PRIORITY-DATA:

COUNTRY	APPL-NO	DOC-ID	APPL-DATE
JP	2000-282968	2000JP-2000-282968	September 19, 2000
JP	2000-359192	2000JP-2000-359192	November 27, 2000
JP	2001-122164	2001JP-2001-122164	April 20, 2001
JP	2001-252268	2001JP-2001-252268	August 23, 2001

INT-CL: [07], H01M010/40 , H01G009/038

US-CL-PUBLISHED: 429/303, 429/314 , 429/317 , 361/502 ,  
361/526

US-CL-CURRENT: 429/303, 361/502 , 361/526 , 429/314 ,  
429/317

REFERENCE-FIGURES: 2

ABSTRACT:

An ion-conductive composition includes an electrolyte solution made of an ion-conductive salt and a solvent in which the ion-conductive salt is soluble, and a thermoplastic resin having a specific swelling ratio when immersed in the electrolyte solution. The invention is also directed at a gel electrolyte produced by shaping the thermoplastic resin, then immersing it in an electrolyte solution to effect swelling. High-performance non-aqueous electrolyte batteries and electrical double-layer capacitors can be built using a thermoplastic resin-containing electrode binder composition in which the resin bonds well with active materials or activated carbon and which has an excellent adhesion to current conductors.

----- KWIC -----

Detail Description Paragraph - DETX (98):

[0145] The conductive material may be any suitable material capable of conferring electrical conductivity to the polarizable electrode binder composition. Illustrative examples include carbon black, Ketjenblack, acetylene black, carbon whiskers, carbon fibers, natural graphite, artificial graphite, titanium oxide, ruthenium oxide, and metallic fibers such as aluminum or nickel. Any one or combinations of two or more thereof may be used. Of these, Ketjenblack and acetylene black, which are both types of carbon black, are preferred. The average particle size of the conductive material powder is preferably 10 to 100 nm, and especially 20 to 40 nm.